

Pakistan Standard Specification for

Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement



(ALL RIGHTS RESERVED)

PAKISTAN STANDARDS AND QUALITY CONTROL AUTHORITY

STANDARDS DEVELOPMENT CENTRE

STANDARDIZATION WING

1ST FLOOR, ST-7-A, BLOCK-3

GULISTAN-E-JOHER

Karachi

Pakistan Standard Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement

FOREWORD:

- 0.1 This Standard was adopted by Pakistan Standard & Quality Control Authority after recommendations of the Technical Committee for “**Structural Steel and Concrete Reinforcement (BDC-04)**” dated **26-01-2021**. The same had been approved and endorsed by the Civil Engineering National Standards Committee (CENSC) on 15-07-2021.
- 0.2 This Standard has been prepared after taking into consideration the views and suggestions of the manufacturers, technologists, suppliers and utilizing agencies.
- 0.3 This Pakistan Standard No. **P.S. 1879-2018R** was prepared with the help of foreign specification which has been since revised/modified. Hence to keep up a par with the latest technology, it has been revised accordingly. In preparation of this Standard the Technical Committee acknowledges with thanks the assistance drawn from the standard **ASTM: A-615-2020**.
- 0.4 This Standard is subject to periodical review in order to keep pace with development in industry. Any suggestions for improvement will be recorded and placed before the committee in due course.

NAME OF TECHNICAL COMMITTEE MEMBERS AND THEIR ADDRESSES OF STRUCTURAL STEEL AND CONCRETE REINFORCEMENT (BDC-04)

<p>Engr. Arif Kasam Chief Executive/Chairman (BDC-04) Arif & Associates Consultants C – 84, Block-8, Gulshan-e-Iqbal, Karachi. Cell No.0300-2110466 arifkasamy@yahoo.com</p>	
<p>Ref. No. SDC-2/BDC-04/2018 The Vice Chancellor Quaid-e-Awam University of Engineering Science & Technology, Nawabshah.</p>	<p>Ref. No. SDC-2/BDC-04/2018 The Principal Govt. College of Technology Shershah, S.I.T.E., Karachi. Engr. Kamran Rahat 03159222848</p>
<p>Ref. No. SDC-2/BDC-04/2018 Engr. Aqeel Ahmed Consultant, Civil Engineer Pakistan Steel, Karachi. Cell No.0334-3071558 aqeelahmedkk@gmail.com</p>	<p>Ref. No. SDC-2/BDC-04/2018 Mr. Hamid Maker Consumer Protection Council (CPC) The Helpline Trust, 15-C, 12-Ittehad Lane, Phase-II, Extension DHA, Karachi.</p>
<p>Ref. No. SDC-2/BDC-04/2018 The Vice President NESPAK, 13th Floor NIC Building, Abbasi Shaheed Road Off. Shahrah-e-Faisal Karachi. 99207277-84 karachi@nespak.com.pk nespakkh@khi.wol.net.pk</p>	<p>Ref. No. SDC-2/BDC-04/2018 The Director Nawab Brothers D-41, S.I.T.E, Karachi. sales@nawabsteel.com Ph No.32574084, 32570319</p>
<p>Ref. No. SDC-2/BDC-04/2018 The Chairman Council for Works and Housing Research F – 40, SITE, Hub River Road, Karachi. Amir 0333-2347198</p>	<p>Ref. No. SDC-2/BDC-04/2018 The Director General PCSIR Laboratories Off. University Road Karachi. 021-99261904-11, 021-99261922 – 99261921 dqkic@pcsir.gov.pk dq@pcsir-khi.gov.pk</p>
<p>Ref. No. SDC-2/BDC-04/2018 The General Manager (Technical) Magna Steel (Pvt.) Ltd, 19, Banglore Town, Block 7/8, K.C.H.S.,</p>	<p>Ref. No. SDC-2/BDC-04/2018 The Manager, New Shalimar Steel Industries (Pvt.) Ltd., F-765/C, S.I.T.E, Mauripur Road,</p>

Karachi. info@magnasteel.com.pk 0321-8256042	Karachi. 021-32588112, 32588113, 32588114
Ref. No. SDC-2/BDC-04/2018 Mr. Khalid Khan, Chief Operating Officer, Abbas Steel Group, 123 Old Clifton, Karachi. 0300-8226913	Ref. No. SDC-2/BDC-04/2018 Dewan Abu Obaida Farooqui Senior Vice - Chairman MS Dewan Steel Mills, D-32-SITE, Karachi. Phone: 021-32570811, 325570859 Email: dewanfarooqui@yahoo.com
Ref. No. SDC-2/BDC-04/2018 Mr. Irshad Mowjee, Director, Razaque Steel (Pvt.) Ltd., B-30 (B) Estate Avenue, Shershah S.I.T.E, Karachi-75700. Ph No.021-32561106-09 Irshad-mojee@razaquesteel.com	Mr. Akhtar Saeed Vice Chairman – Karachi Circle M/s Majeed & Sons Steel (Pvt.) Ltd. F-282, S.I.T.E., Karachi. Phone: 021-32571218, 32577273 rolling@cyber.net.pk
Ref. No. SDC-2/BDC-04/2018 Engr. Samiullah Mughal Additional Registrar Pakistan Engg. Council (PEC), ST – 14A, Block-2, KDA Scheme – V, Kehkashan, Clifton, Karachi. karachi@pec.org.pk Phone: +(92-21) 35834970 Cell No.0333-2169825	Ref. No. SDC-2/BDC-04/2018 Sheikh Khurram Ishtiaq Chairman, Pakistan Steel Re- Rolling Mills Association, 407, S. S. Chamber Estate Avenue, S.I.T.E, Karachi. Ph. No.021-32572511 Info.psrma_kar@yahoo.com khurram@nawabsteel.com
Ref. No. SDC-2/BDC-04/2018 The General Manager Quality Control Peoples Steel Mills Ltd. Manghopir, Karachi - 75890 36770116 - 18 & 31- 33 36770126 - 28 marketing@psmltd.com	Ref. No. SDC-2/BDC-04/2018 Syed Ali Raza Dy. Director (Physical) Quality Control Centre PSQCA, Karachi. Cell No.0333-3284491 S_aliraza786@yahoo.com
Ref. No. SDC-2/BDC-04/2018 The Registrar Mehran Engineering of Engineering and Technology Jamshoro- 76062 registrar@admin.muett.edu.pk phone: +92 22 2771371	Ref. No. SDC-2/BDC-04/2018 The Secretary, Pakistan Steel Re-Rolling Mills 24-25, Sector 1-9, Industrial Area, Islamabad. info@ittehad.com.pk info@shalimarsteel.com

	rolling@cyber.net.pk dewanfarooqui@yahoo.com rolling@cyber.net.pk
Ref. No. SDC-2/BDC-04/2018 Engr. Bawer Tawfik Millwala Dredging Co. Private Ltd. Steel House, West Wharf Road Karachi 74000. Cell:0300-9206272, 021-32800225-6 Email: bt@millwaladredging.com	Ref. No. SDC-2/BDC-04/2018 Mr. Kashif Ayub Vice Chairman, Pakistan Steel Re-Rolling Mills Association, 407, S.S.Chamber Estate Avenue, S.I.T.E., Karachi. Cell No.0321-8258759 kashif@citysteel.pk
Ref. No. SDC-2/BDC-04/2018 Mr. Khurshid Khilji General Manager (Technical), Magna Steel (Pvt.) Ltd, 19, Banglore Town, Block 7/8, K.C.H.S., Karachi. info@magnasteel.com.pk 0321-8256042	Ref. No. SDC-2/BDC-04/2018 Mr. Sahibzada M. Junaid Bacha, Chief Relationship Officer, Frontier Foundry (Pvt.) Ltd., Unit I, Plot No.166, Road B-7, Hyatabad Industrial Estate Peshawar. Cell No.0315-8550347 Ph No.111-888-999, 2244888999 Muhhammad.junaid@ff.com.pk
Ref. No. SDC-2/BDC-04/2018 Engr. Asif Abbasi Assistant Professor Department of Civil Engineering Sir Syed University of Engineering and Technology University Road, Karachi-75300. Ph No.021-34982985 Cell No.0333-2239850 aabbasi@ssuet.edu.pk asifabbasi@outlook.com	Ref. No. SDC-2/BDC-04/2018 Engr. Khalid Khan ASG Metals, Abbas Steel Group, 123-Old Clifton, Karachi. Ph No.021-35870171-2 Cell No.0300-8226913 k.khan@asgpk.com
Ref. No. SDC-2/BDC-04/2018 Mr. Zoeb Salemwala Executive Manager Corporate Affairs Amreli Steels Ltd. A/18, S.I.T.E., Karachi. Ph No.32587232-9 Cell No.0321-8256042 Zoeb.salelmwala@amrelisteels.com	Ref. No. SDC-2/BDC-04/2018 Engr. Amir Nizam Department of Civil Engineering NED University of Engineering and Technology Karachi. Cell No.0300-9253021 amirsahrai@hotmail.com

<p>Ref. No. SDC-2/BDC-04/2018 Dr. A. J. Sangi Professor Civil Engineering Department NED University of Engineering and Technology, Karachi. Cell No.0345-2251155 ajsangi@gmail.com</p>	<p>Ref. No. SDC-2/BDC-04/2018 Mr. Muhammad Yaqoob Aman Steel Manghopir Road, Karachi. Cell No.0323-2782912 mybhuri@yahoo.com amansteel1@gmail.com</p>
<p>Ref. No. SDC-2/BDC-04/2018 Engr. Kamran Rahat Associate Professor STEVTA Govt. College of Technology S.I.T.E. Karachi. Cell No.0315-9222848 Engr.kamran.rahata@hotmail.com</p>	<p>Ref. No. SDC-2/BDC-04/2018 Mr. Mohsin Khan Head of Sales and Marketing Agha Steel Industries Suite # 801 & 804, 8th Floor, Emerald Tower G-19, Block-5, II Talwar Main Clifton Road, Karachi. Cell No.0321-8279196 Ph No.021-34750432 Mohsin.khan@aghasteel.com</p>
<p>Ref. No. SDC-2/BDC-04/2018 Ar. Farhatullah Qureshi Representative of Pakistan Council of Architect and Town Planners 95-B Ground Floor, Block-2, P.E.C.H.S. Karachi. Cell No.0333-3021830 Ph No.021-34300159 Far805@gmail.com</p>	<p>Ref. No. SDC-2/BDC-04/2018 Engr. Syed Amir Ali Sr. Research Officer Council for Works and Housing Research (CWHR) F-40, S.I.T.E. Hub River Road Karachi. Cell No.0333-2347198 Syed029@yahoo.com</p>
<p>Ref. No. SDC-2/BDC-04/2018 Engr. Zubaidullah Research Engineer Council for Works and Housing Research F-40, S.I.T.E. Hub River Road, Karachi. Cell No.0346-9034073 engrzubid@hotmail.com</p>	<p>Ref. No. SDC-2/BDC-04/2018 Dy. Chief Engineer Technical Services Directorate Pakistan Steel, Karachi. Ph No.021 34750903 ts@paksteel.com.pk</p>
<p>Dr. Parwaiz A. A. Khan Dawood University of Engineering and Technology New M. A. Jinnah Road Karachi-74800. Cell No.0333-2127393 parwaizk@yahoo.com</p>	<p>Muhammad Ali Baig Business Development Manager Mughal Iron and Steel Industries Ltd. Badami Bagh Office: 41-Peco Road, Badamin Bagh, Lahore. Ph No.042-111-000-007 Cell No.0300-0644266 supreme@mughalsteel.com</p>

Engr. Rukhsana Rahooja
CWHR (Retd. Chairperson)
207/B, SMCHS, Karachi.
Cell No.0300-2781655
Rukhsana.rahooja@gmail.com
pro.ctfr@gmail.com

The Chairman,
Association of Builders & Developers,
ST – 1/D, Block – 16,
Gulistan-e-Johar, Karachi.
UAN: 111-11-ABAD (2223)
abadsecretariat@yahoo.com

Draft Pakistan Standard Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement

1. Scope

1.1 This specification covers deformed and plain carbon-steel bars in cut lengths and coils for concrete reinforcement. Annex A2 of this specification covers deformed bars for use for other applications. Steel bars containing alloy additions, such as with the Association for Iron and Steel Technology and the Society of Automotive Engineers series of alloy steels, are permitted if the resulting product meets all the other requirements of this specification. The standard sizes and dimensions of deformed bars and their number designations are given in Table 1.

1.2 Unless specified for use for other applications in Annex A2, bars are of four minimum yield strength levels: namely, 40 000 psi [280 MPa], 60 000 psi [420 MPa], 80 000 psi [550 MPa], and 100 000 psi [690 MPa], designated as Grade 40 [280], Grade 60 [420], Grade 80 [550], and Grade 100 [690], respectively.

NOTE 1—Grade 100 [690] reinforcing bars were introduced in this specification in 2015. In contrast to the lower grades, which have ratios of specified tensile strength to specified yield strength that range from 1.25 to 1.50, Grade 100 [690] reinforcing bars have a ratio of specified tensile strength to specified yield strength of 1.15. Users of this specification should be aware that there will, therefore, be a lower margin of safety and reduced warning of failure following yielding when Grade 100 [690] bars are used in structural members where strength is governed by the tensile strength of the reinforcement, primarily in beams and slabs. As a result of the lower specified tensile strength to specified yield strength ratio of 1.15 for Grade 100 [690], users of this specification should be aware that ACI 318 Type 1 mechanical and welded splice requirements found in many acceptance criteria of 125 % of specified yield strength requirements in tension and compression are not applicable to Grade 100 [690]. Mechanical and welded splices should meet a minimum specified tensile strength of 115 000 psi [790 MPa] for Grade 100 [690].

NOTE 2—Users of this specification need to be aware that consensus design codes and specifications may not recognize the use of the No. 20 [64] bar, the largest bar included in this specification. Structural members reinforced with No. 20 [64] bars may require approval of the building official or other appropriate authority and require special detailing to ensure adequate performance at service and factored loads.

1.3 Plain bars, in sizes up to and including 2½ in. [63.5 mm] in diameter in coils or cut lengths, when ordered shall be furnished under this specification in Grade 40 [280], Grade 60 [420], Grade 80 [550], and Grade 100 [690]. For ductility properties (elongation and bending), test provisions of the nearest smaller nominal diameter deformed bar size shall apply. Requirements providing for deformations and marking shall not be applicable.

NOTE 3—Welding of the material in this specification should be approached with caution since no specific provisions have been included to enhance its weldability. When this steel is to be welded, a welding procedure suitable for the chemical composition and intended use or service should be used. The use of the latest edition of AWS D1.4/D1.4M is recommended. The AWS D1.4/D1.4M Welding Code describes the proper selection of the filler metals and preheat/interpass temperatures, as well as performance and procedure qualification requirements.

1.4 Requirements for alternate bar sizes are presented in Annex A1. The requirements in Annex A1 only apply when specified by the purchaser (see 4.2.4).

1.5 The text of this specification references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables) shall not be considered as requirements of the specification.

1.6 This specification is applicable for orders in either inch-pound units (as Specification A615) or in SI units (as Specification A615M).

1.7 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the specification.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 Pakistan Standards / ASTM Standards:

PS.../ASTM A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling

PS/ASTM:A370-2013 Test Methods and Definitions for Mechanical Testing of Steel Products

PS.../ASTMA510/A510M Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel, and Alloy Steel

PS/ASTM A700-2009 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment

PS:4994-2014R/ASTMA706 Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement

PS.../ASTMA751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

PS/ASTM E29-2013 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

PS.../ASTME290 Test Methods for Bend Testing of Material for Ductility

2.2 ACI Standard:

ACI 318 Building Code Requirements for Structural Concrete

2.3 AWS Standard:

AWS D1.4/D1.4M Structural Welding Code—Reinforcing Steel

2.4 U.S. Military Standard:

MIL-STD-129 Marking for Shipment and Storage

2.5 U.S. Federal Standard:

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

TABLE 1 Deformed Bar Designation Numbers, Nominal Weights [Masses], Nominal Dimensions, and Deformation Requirements

Bar Designation No.	Nominal Weight, lb/ft [Nominal Mass, kg/m]	Nominal Dimensions ^A			Deformation Requirements, in. [mm]		
		Diameter, in. [mm]	Cross-Sectional Area, in. ² [mm ²]	Perimeter, in. [mm]	Maximum Average Spacing	Minimum Average Height	Maximum Gap (Chord of 12.5 % of Nominal Perimeter)
3 [10]	0.376 [0.560]	0.375 [9.5]	0.11 [71]	1.178 [29.9]	0.262 [6.7]	0.015 [0.38]	0.143 [3.6]
4 [13]	0.668 [0.994]	0.500 [12.7]	0.20 [129]	1.571 [39.9]	0.350 [8.9]	0.020 [0.51]	0.191 [4.9]
5 [16]	1.043 [1.552]	0.625 [15.9]	0.31 [199]	1.963 [49.9]	0.437 [11.1]	0.028 [0.71]	0.239 [6.1]
6 [19]	1.502 [2.235]	0.750 [19.1]	0.44 [284]	2.356 [59.8]	0.525 [13.3]	0.038 [0.97]	0.286 [7.3]
7 [22]	2.044 [3.042]	0.875 [22.2]	0.60 [387]	2.749 [69.8]	0.612 [15.5]	0.044 [1.12]	0.334 [8.5]
8 [25]	2.670 [3.973]	1.000 [25.4]	0.79 [510]	3.142 [79.8]	0.700 [17.8]	0.050 [1.27]	0.383 [9.7]
9 [29]	3.400 [5.060]	1.128 [28.7]	1.00 [645]	3.544 [90.0]	0.790 [20.1]	0.056 [1.42]	0.431 [10.9]
10 [32]	4.303 [6.404]	1.270 [32.3]	1.27 [819]	3.990 [101.3]	0.889 [22.6]	0.064 [1.63]	0.487 [12.4]
11 [36]	5.313 [7.907]	1.410 [35.8]	1.56 [1006]	4.430 [112.5]	0.987 [25.1]	0.071 [1.80]	0.540 [13.7]
14 [43]	7.65 [11.38]	1.693 [43.0]	2.25 [1452]	5.32 [135.1]	1.185 [30.1]	0.085 [2.16]	0.648 [16.5]
18 [57]	13.60 [20.24]	2.257 [57.3]	4.00 [2581]	7.09 [180.1]	1.58 [40.1]	0.102 [2.59]	0.864 [21.9]
20 [64] ^B	16.69 [24.84]	2.500 [63.5]	4.91 [3167]	7.85 [199.5]	1.75 [44.5]	0.113 [2.86]	0.957 [24.3]

^A The nominal dimensions of a deformed bar are equivalent to those of a plain round bar having the same weight [mass] per foot [metre] as the deformed bar.

^B Refer to Note 2.

3. Terminology

3.1 Definitions of Terms Specific to This Specification:

3.1.1 *deformations, n*—transverse protrusions on a deformed bar.

3.1.2 *deformed bar, n*—steel bar with protrusions; a bar that is intended for use as reinforcement in reinforced concrete construction.

3.1.2.1 *Discussion*—The surface of the bar is provided with protrusions that inhibit longitudinal movement of the bar relative to the concrete surrounding the bar in such construction. The protrusions conform to the provisions of this specification.

3.1.3 *plain bar, n*—steel bar without protrusions.

3.1.4 *rib, n*—longitudinal protrusion on a deformed bar.

4. Ordering Information

4.1 Orders for carbon-steel bars for concrete reinforcement under this specification shall contain the following information:

4.1.1 Quantity (weight) [mass],

4.1.2 Deformed or plain,

4.1.3 Bar designation number (size) of deformed bars, or nominal diameter (size) of plain bars

4.1.4 Cut lengths or coils,

4.1.5 Grade, and

4.1.6 ASTM designation A615 [A615M] and year of issue.

4.2 The purchaser shall have the option to specify additional requirements, including but not limited to, the following:

4.2.1 Requirements for inspection (17.1),

4.2.2 Require bars in each bundle to be supplied from a single heat (19.1),

4.2.3 Special package marking requirements (20.2),

4.2.4 Requirements for alternative bar sizes in Annex A1,

4.2.5 Requirements for bars for other applications in Annex A2, and 4.2.6 Other special requirements, if any.

5. Material and Manufacture

5.1 The bars shall be rolled from properly identified heats of mold-cast or strand-cast steel. The steel shall be made by any commercially accepted process.

6. Chemical Composition

6.1 The chemical analysis of each heat of steel shall be determined in accordance with Test Methods, Practices, and Terminology A751. The manufacturer shall make the analysis on test samples taken preferably during the pouring of the heat. The percentages of carbon, manganese, phosphorus, and sulfur shall be determined. The phosphorus content thus determined shall not exceed 0.06 %.

6.2 A product check, for phosphorus, made by the purchaser shall not exceed that specified in 6.1 by more than 25%.

7. Requirements for Deformations

7.1 Deformations shall be spaced along the bar at substantially uniform distances. The deformations on opposite sides of the bar shall be similar in size, shape, and pattern.

7.2 The deformations shall be placed with respect to the axis of the bar so that the included angle is not less than 45°. Where the line of deformations forms an included angle with the axis of the bar from 45 to 70° inclusive, the deformations shall alternately reverse in direction on each side, or those on one side shall be reversed in direction from those on the opposite side. Where the line of deformations is over 70°, a reversal in direction shall not be required.

7.3 The average spacing or distance between deformations on each side of the bar shall not exceed seven tenths of the nominal diameter of the bar.

7.4 The overall length of deformations shall be such that the gap (measured as a chord) between the ends of the deformations shall not exceed 12.5 % of the nominal perimeter of the bar. Where the ends terminate in a rib, the width of the rib shall be considered as the gap between these ends. The summation of the gaps shall not exceed 25 % of the nominal perimeter of the bar. The nominal perimeter of the bar shall be 3.1416 times the nominal diameter.

7.5 The spacing, height, and gap of deformations shall conform to the requirements prescribed in Table 1.

8. Measurements of Deformations

8.1 The average spacing of deformations shall be determined by measuring the length of a minimum of ten spaces and dividing that length by the number of spaces included in the measurement. The measurement shall begin from a point on a deformation at the beginning of the first space to a corresponding point on a deformation after the last included space. Spacing measurements shall not be made over a bar area containing bar marking symbols involving letters or numbers.

8.2 The average height of deformations shall be determined from measurements made on not less than two typical deformations. Determinations shall be based on three measurements per deformation, one at the center of the overall length and the other two at the quarter points of the overall length.

8.3 Insufficient height, insufficient circumferential coverage, or excessive spacing of deformations shall not constitute cause for rejection unless it has been clearly established by determinations on each lot (Note 4) tested that typical deformation height, gap, or spacing do not conform to the minimum requirements prescribed in Section 7. No rejection shall be made on the basis of measurements if fewer than ten adjacent deformations on each side of the bar are measured.

NOTE 4—As used within the intent of 8.3, the term “lot” shall mean all the bars of one bar size and pattern of deformations contained in an individual shipping release or shipping order.

9. Tensile Requirements

9.1 The material, as represented by the test specimens, shall conform to the requirements for tensile properties prescribed in Table 2.

TABLE 2 Tensile Requirements

	Grade 40 [280] ^A	Grade 60 [420]	Grade 80 [550]	Grade 100 [690]
Tensile strength, min, psi [MPa]	60 000 [420]	80 000 [550]	100 000 [690]	115 000 [790]
Yield strength, min, psi [MPa]	40 000 [280]	60 000 [420]	80 000 [550]	100 000 [690]
Ratio of actual tensile strength to actual yield strength, min	1.10	1.10	1.10	1.10
Elongation in 8 in. [200 mm], min, %				
Bar Designation No.				
3 [10]	11	9	7	7
4, 5 [13, 16]	12	9	7	7
6 [19]	12	9	7	7
7, 8 [22, 25]	...	8	7	7
9, 10, 11 [29, 32, 36]	...	7	6	6
14, 18, 20 [43, 57, 64]	...	7	6	6

^A Grade 40 [280] bars are furnished only in sizes 3 through 6 [10 through 19].

TABLE 3 Bend Test Requirements

Bar Designation No.	Pin Diameter for Bend Tests ^A			
	Grade 40 [280]	Grade 60 [420]	Grade 80 [550]	Grade 100 [690]
3, 4, 5 [10, 13, 16]	3½ <i>d</i> ^B	3½ <i>d</i>	5 <i>d</i>	5 <i>d</i>
6 [19]	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>
7, 8 [22, 25]	...	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>
9, 10, 11 [29, 32, 36]	...	7 <i>d</i>	7 <i>d</i>	7 <i>d</i>
14, 18 [43, 57] (90°)	...	9 <i>d</i>	9 <i>d</i>	9 <i>d</i>
20 [64] (90°)	...	10 <i>d</i>	10 <i>d</i>	...

^A Test bends 180° unless noted otherwise.

^B *d* = nominal diameter of specimen.

9.2 The yield point or yield strength shall be determined by one of the following methods:

9.2.1 The yield point shall be determined by the drop or halt of the gauge of the tensile testing machine, where the steel tested has a sharp-knead or well-defined yield point.

9.2.2 Where the steel tested does not have a well-defined yield point, the yield strength shall be determined by the offset method (0.2 % offset), as described in Test Methods and Definitions **A370**.

9.3 When material is furnished in coils, the test specimen shall be taken from the coil and straightened prior to placing it in the jaws of the tensile testing machine. (See Note 5.)

NOTE 5—Straighten the test specimen to avoid formation of local sharp bends and to minimize cold work. Insufficient straightening prior to attaching the extensometer can result in lower-than-actual yield strength readings.

9.3.1 Test specimens taken from post-fabricated material shall not be used to determine conformance to this specification. (See Note 6.)

NOTE 6—Multiple bending distortion from mechanical straightening and fabricating machines can lead to excessive cold work, resulting in higher yield strengths, lower elongation values, and a loss of deformation height.

9.4 The percentage of elongation shall be as prescribed in Table 2.

10. Bending Requirements

10.1 The bend-test specimen shall withstand being bent around a pin without cracking on the outside radius of the bent portion. The requirements for degree of bending and sizes of pins are prescribed in Table 3. When material is furnished in coils, the test specimen shall be straightened prior to placing it in the bend tester.

10.2 The bend test shall be made on specimens of sufficient length to ensure free bending and with apparatus that provides:

10.2.1 Continuous and uniform application of force throughout the duration of the bending operation.

10.2.2 Unrestricted movement of the specimen at points of contact with the apparatus and bending around a pin free to rotate.

10.2.3 Close wrapping of the specimen around the pin during the bending operation.

10.3 It shall be permissible to use other methods of bend testing as described in Test Methods **E290**, such as placing a specimen across two round bearings free to rotate and applying

the bending force with a fixed rounded-tip mandrel conforming to the specified bend radius, allowing the bar to pass through with sufficient clearance. When failures occur under other methods of bend testing, retests shall be permitted under the bend-test method prescribed in 10.2.

11. Permissible Variation in Weight [Mass]

11.1 Deformed reinforcing bars shall be evaluated on the basis of nominal weight [mass]. The weight [mass] determined using the measured weight [mass] of the test specimen and rounding in accordance with Practice **PS/ASTM E29-2013**, shall be at least

94 % of the applicable weight [mass] per unit length prescribed in Table 1. In no case shall overweight [excess mass] of any deformed bar be the cause for rejection.

11.2 Weight [mass] variation for plain bars shall be computed on the basis of permissible variation in diameter. For plain bars smaller than $\frac{3}{8}$ in. [9.5 mm] in diameter, use Specification **PS.../ASTMA510/A510M**. For larger plain bars up to and including $2\frac{1}{2}$ in. [63.5 mm] in diameter, use Specification **PS.../ASTMA6/A6M**.

12. Finish

12.1 The bars shall be free of detrimental surface imperfections.

12.2 Rust, seams, surface irregularities, or mill scale shall not be cause for rejection, provided the weight [mass], nominal dimensions, cross-sectional area, and tensile properties of a hand wire brushed test specimen are not less than the requirements of this specification.

12.3 Surface imperfections or flaws other than those specified in 12.2 shall be considered detrimental when specimens containing such imperfections fail to conform to either tensile or bending requirements. Examples include, but are not limited to, laps, seams, scabs, slivers, cooling or casting cracks, and mill or guide marks.

NOTE 7—Deformed reinforcing bars intended for epoxy coating applications should have surfaces with a minimum of sharp edges to achieve proper coverage. Particular attention should be given to bar marks and deformations where coating difficulties are prone to occur.

NOTE 8—Deformed reinforcing bars destined to be mechanically-spliced or butt-spliced by welding may require a certain degree of roundness in order for the splices to adequately achieve strength requirements.

13. Number of Tests

13.1 One tension test and one bend test shall be made of each bar size rolled from each heat.

13.2 One set of dimensional property tests including bar weight [mass] and spacing, height, and gap of deformations shall be made of each bar size rolled from each heat.

14. Retests

14.1 If the results of an original tension test specimen fail to meet the specified minimum requirements and are within 2000 psi [14 MPa] of the required tensile strength, within 1000 psi [7 MPa] of the required yield strength, or within two percentage units of the required elongation, a retest shall be permitted on two random specimens for each original tension test specimen failure from the lot. Both retest specimens shall meet the requirements of this specification.

14.2 If a bend test fails for reasons other than mechanical reasons or flaws in the specimen as described in 14.4.2 and 14.4.3, a retest shall be permitted on two random specimens from the same lot. Both retest specimens shall meet the requirements of this specification. The retest shall be performed on test specimens that are at air temperature but not less than 60°F [16°C].

14.3 If a weight [mass] test fails for reasons other than flaws in the specimen as described in 14.4.3, a retest shall be permitted on two random specimens from the same lot. Both retest specimens shall meet the requirements of this specification.

14.4 If the original test or any of the random retests fails because of any reasons listed in 14.4.1, 14.4.2, or 14.4.3, the test shall be considered an invalid test:

14.4.1 The elongation property of any tension test specimen is less than that specified, and any part of the fracture is outside the middle half of the gage length, as indicated by scribe marks on the specimen before testing;

NOTE 9—Marking specimens with multiple scribe or punch marks can reduce the occurrence of fracture outside or near these marks and the need for declaring the test invalid.

14.4.2 Mechanical reasons such as failure of testing equipment or improper specimen preparation; and

14.4.3 Flaws are detected in a test specimen, either before or during the performance of the test.

14.5 The original results from 14.4.1, 14.4.2, or 14.4.3 shall be discarded and the test shall be repeated on a new specimen from the same lot.

15. Test Specimens

15.1 All mechanical tests shall be conducted in accordance with Test Methods and Definitions **PS/ASTM:A370-2013**. In case of any conflict between the requirements in this specification and the requirements of Test Methods and Definitions **PS/ASTM:A370-2013**, the requirements in this specification shall prevail.

15.2 Tension test specimens shall be the full section of the bar as rolled. Unit stress determinations for yield and tensile strength shall be based on the nominal bar area.

15.2.1 Tension test specimens shall be long enough to provide for an 8-in. [200-mm] gage length, a distance of at least two bar diameters between each gage mark and the grips.

NOTE 10—It is recommended that sufficient additional length of the test

specimen be provided to fill the grips completely, leaving some excess length protruding beyond each grip. The grips should be shimmed so that no more than ½ in. [13 mm] of a grip protrudes from the head of the tensile testing machine.

15.2.2 *Gage Marks*—The 8-in. [200-mm] gage length shall be marked on the specimen using a preset 8-in. [200-mm] punch or, alternately, may be punch marked every 2 in. [50 mm] along the 8-in. [200-mm] gage length, on one of the longitudinal ribs, if present, or in the clear spaces between transverse deformations. Punch marks shall not be placed on a transverse deformation.

NOTE 11—Light punch marks are desirable because deep marks severely indent the bar and may affect the results.

15.3 Bend test specimens shall be the full section of the bar as rolled.

16. Test Reports

16.1 The following information shall be reported on a per heat basis. Report additional items as requested or desired.

16.1.1 Chemical analysis including the percentages of carbon, manganese, phosphorus, and sulfur.

16.1.2 Tensile properties.

16.1.3 Bend test results.

16.2 A Material Test Report, Certificate of Inspection, or similar document printed from or used in electronic form from an electronic data interchange (EDI) transmission shall be regarded as having the same validity as a counterpart printed in the certifier's facility. The content of the EDI transmitted document shall meet the requirements of the invoked ASTM standard(s) and conform to any EDI agreement between the purchaser and the manufacturer. Notwithstanding the absence of a signature, the organization submitting the EDI transmission is responsible for the content of the report.

NOTE 12—The industry definition invoked here is: EDI is the computer to computer exchange of business information in a standard format such as ANSI ASC X12.

17. Inspection

17.1 Inspection of the carbon-steel reinforcing bars shall be agreed upon between the purchaser and the manufacturer as part of the purchase order or contract.

18. Rejection and Rehearing

18.1 Any rejection based on testing undertaken by the purchaser shall be promptly reported to the manufacturer.

18.2 Samples tested that represent rejected material shall be preserved for two weeks from the date rejection is reported to the manufacturer. In case of dissatisfaction with the results of the tests, the manufacturer shall have the right to make claim for a rehearing within that time.

19. Marking

19.1 When loaded for mill shipment, bars shall be properly separated and tagged with the manufacturer's heat or test identification number. Unless otherwise specified, it shall be permissible for the manufacturer to make a full-size bundle at the end of a heat by adding bars from a consecutively rolled

heat of the same nominal chemical composition. The manufacturer shall identify a bundle consisting of bars from two heats with the identification number of the first heat rolled or identify both heats. The manufacturer shall maintain records of the heats contained in each bundle.

NOTE 13—It is recommended that the manufacturer provide mill certificates from both heats in bundle.

19.2 Each manufacturer shall identify the symbols of their marking system.

19.3 All bars produced to this specification, except plain bars which shall be tagged for grade, shall be identified by a distinguishing set of marks legibly rolled onto the surface of one side of the bar to denote in the following order:

19.3.1 *Point of Origin*—Letter or symbol established as the manufacturer’s mill designation.

19.3.2 *Size Designation*—Arabic number corresponding to bar designation number of Table 1.

19.3.3 *Type of Steel*—Letter *S* indicating that the bar was produced to this specification, or for Grades 60 [420] and 80 [550] bars only, letters *S* and *W* indicating that the bar was produced to meet both this specification and Specification **PS:4994-2014R/ASTMA706**.

19.3.4 *Minimum Yield Strength Designation*—For Grade 60 [420] bars, either the number 60 [4] or a single continuous longitudinal line through at least five deformation spaces offset from the center of the bar side. For Grade 80 [550] bars, either

the number 80 [6] or three continuous longitudinal lines through at least five deformation spaces. For Grade 100 [690] bars, either the number 100 [7] or four continuous lines through at least five deformation spaces, or the letter *C*. No marking designation is required for Grade 40 [280] bars.

19.3.5 It shall be permissible to substitute: a metric size bar of Grade 280 for the corresponding inch-pound size bar of Grade 40, a metric size bar of Grade 420 for the corresponding inch-pound size bar of Grade 60, a metric size bar of Grade 550 for the corresponding inch-pound size bar of Grade 80, and a metric size bar of Grade 690 for the corresponding inch-pound size bar of Grade 100.

20. Packaging and Package Marking

20.1 Packaging, marking, and loading for shipment shall be in accordance with Practices **PS/ASTM A700-2009**.

20.2 When specified in the purchase order or contract, and for direct procurement by or direct shipment to the U.S. Government, marking for shipment, in addition to requirements specified in the purchase order or contract, shall be in accordance with MIL-STD-129 for military agencies and with Fed. Std. No. 123 for civil agencies.

21. Keywords

21.1 concrete reinforcement; deformations (protrusions); steel bars

ANNEXES

(Mandatory Information) A1.

ALTERNATE BAR SIZES

A1.1 The following requirements shall apply only when specified in the purchase order or contract. When specified, the

following Table A1.1, Table A1.2, and Table A1.3 replace Table 1, Table 2, and Table 3, respectively.

TABLE A1.1 Deformed Bar Designations, Nominal Weights [Masses], Nominal Dimensions, and Deformation Requirements

Bar Designation No. ^A	Nominal Weight, lb/ft ^B [Nominal Mass, kg/m] ^C	Nominal Dimensions ^D			Deformation Requirements, in. [mm]		
		Diameter, in. [mm]	Cross-Sectional Area, in. ² [mm ²]	Perimeter, in. [mm]	Maximum Average Spacing	Minimum Average Height	Maximum Gap (Chord of 12.5 % of Nominal Perimeter)
10	0.414 [0.617]	0.394 [10.0]	0.12 [79]	1.237 [31.4]	0.276 [7.0]	0.016 [0.40]	0.151 [3.8]
12	0.597 [0.888]	0.472 [12.0]	0.18 [113]	1.484 [37.7]	0.331 [8.4]	0.019 [0.48]	0.181 [4.6]
16	1.061 [1.578]	0.630 [16.0]	0.31 [201]	1.979 [50.3]	0.441 [11.2]	0.028 [0.72]	0.241 [6.1]
20	1.657 [2.466]†	0.787 [20.0]	0.49 [314]	2.474 [62.8]	0.551 [14.0]	0.039 [1.00]	0.301 [7.7]
25	2.589 [3.853]	0.984 [25.0]	0.76 [491]	3.092 [78.5]	0.689 [17.5]	0.049 [1.25]	0.377 [9.6]
28	3.248 [4.834]	1.102 [28.0]	0.95 [616]	3.463 [88.0]	0.772 [19.6]	0.055 [1.40]	0.422 [10.7]
32	4.242 [6.313]	1.260 [32.0]	1.25 [804]	3.958 [100.5]	0.882 [22.4]	0.063 [1.60]	0.482 [12.2]
36	5.369 [7.990]	1.417 [36.0]	1.58 [1018]	4.453 [113.1]	0.992 [25.2]	0.071 [1.80]	0.542 [13.8]
40	6.629 [9.865]	1.575 [40.0]	1.95 [1257]	4.947 [125.7]	1.102 [28.0]	0.79 [2.00]	0.603 [15.3]
50	10.36 [15.41]	1.969 [50.0]	3.04 [1963]	6.184 [157.1]	1.378 [35.0]	0.098 [2.50]	0.753 [19.1]
60	14.91 [22.20]	2.362 [60.0]	4.38 [2827]	7.421 [188.5]	1.654 [42.0]	0.106 [2.70]	0.904 [23.0]

† Editorially corrected.

^A The bar designations are based on the number of millimetres of the nominal diameter of the bar.

^B The assumed weight of a cubic foot of steel is 490 lb/ft³ in accordance with Specification A6/A6M.

^C The assumed mass of a cubic metre of steel is 7850 kg/m³ in accordance with Specification A6/A6M.

^D The nominal dimensions of a deformed bar are equivalent to those of a plain round bar having the same weight [mass] per foot [metre] as the deformed bar.

TABLE A1.2 Tensile Requirements

	Grade 40 [280] ^A	Grade 60 [420]	Grade 80 [550]	Grade 100 [690]
Tensile strength, min, psi [MPa]	60 000 [420]	80 000 [550]	100 000 [690]	115 000 [790]
Yield strength, min, psi [MPa]	40 000 [280]	60 000 [420]	80 000 [550]	100 000 [690]
Ratio of actual tensile strength to actual yield strength, min	1.10	1.10	1.10	1.10
Elongation in 8 in. [200 mm], min, %				
Bar Designation No.				
10	11	9	7	7
12, 16	12	9	7	7
20	12	9	7	7
25	...	8	7	7
28, 32, 36	...	7	6	6
40, 50, 60	...	7	6	6

^A Only bar sizes 10 through 20 are covered by this specification for Grade 40 [280].

TABLE A1.3 Bend Test Requirements

Bar Designation No.	Grade 40 [280]	Grade 60 [420]	Grade 80 [550]	Grade 100 [690]
10, 12, 16	$3\frac{1}{2} d^B$	$3\frac{1}{2} d$	$5d$	$5d$
20	$5d$	$5d$	$5d$	$5d$
25	...	$5d$	$5d$	$5d$
28, 32, 36	...	$7d$	$7d$	$7d$
40, 50, 60 (90°)	...	$9d$	$9d$	$9d$

^A Test bends 180° unless noted otherwise.

^B d = nominal diameter of specimen.

A2. BARS FOR MINE ROOF AND ROCK BOLTS AND OTHER APPLICATIONS

A2.1 The following requirements shall apply only when specified in the purchase order or contract for bars used to fabricate bars for other applications.

A2.2 Bars for other applications are of one minimum yield strength level: namely, 75 000 psi [520 MPa], designated as Grade 75 [520].

A2.3 When specified, Table A2.1 and Table A2.2 shall replace Table 2 and Table 3, respectively.

A2.4 *Minimum Yield Strength Designation*—For Grade 75 [520] bars, either the number 75 [5] or two continuous longitudinal lines through at least five deformation spaces offset each direction from the center of the bar.

A2.5 It shall be permissible to substitute a metric size bar of Grade 520 for the corresponding inch-pound size bar of Grade 75.

TABLE A2.1 Tensile Requirements

	Grade 75 [520]
Tensile strength, min, psi [MPa]	100 000 [690]
Yield strength, min, psi [MPa]	75 000 [520]
Elongation in 8 in. [200 mm], min, %	
Bar Designation No.	
3 [10]	7
4, 5 [13, 16]	7
6 [19]	7
7, 8 [22, 25]	7
9, 10, 11 [29, 32, 36]	6
14, 18, 20 [43, 57, 64]	6

TABLE A2.2 Bend Test Requirements

Bar Designation No.	Pin Diameter for Bend Tests ^A
	Grade 75 [520]
3, 4, 5 [10, 13, 16]	5 <i>d</i> ^B
6 [19]	5 <i>d</i>
7, 8 [22, 25]	5 <i>d</i>
9, 10, 11 [29, 32, 36]	7 <i>d</i>
14, 18 [43, 57] (90°)	9 <i>d</i>
20 [64] (90°)	10 <i>d</i>

^A Test bends 180° unless noted otherwise.

^B *d* = nominal diameter of specimen.

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A615/A615M – 18^{e1}) that may impact the use of this standard. (Approved Apr. 1, 2020.)

(1) Revised Note 1 and Note 2, Section 4, Table 2 and Table A1.2, and Annex A2 Title.