

PAKISTAN STANDARD

Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V

Part-6: Lift cables and cables for flexible connections



(All Rights Reserved)

**PAKISTAN STANDARDS AND QUALITY CONTROL AUTHORITY,
STANDARDS DEVELOPMENT CENTRE,
PSQCA Complex Street 7 A Block -3
Scheme -36 Gulistan -e- johar Karachi**

Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V

Part-7: Flexible cables screened and unscreened with two or more conductors

0. FOREWORD

- 0.1 This Pakistan Standard was adopted by the authority of the Board of Directors of Pakistan Standard and Quality Control Authority after the draft prepared by the Technical Committee for “**Electric Cables**” (TC-7)” had been approved and endorsed by the National Standards Committee on 27 June 2007.
- 0.2 This Pakistan Standard was adopted on the basis of IEC: 60227-7- since IEC Standard have been established in 2011, hence it is deemed necessary to adopt the International standard to keep abreast with the latest technology and as par with IEC standard.
- 0.3 This Pakistan Standard is an adoption of IEC: 60227-7-2007 Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V Part-7 Flexible cables screened and unscreened with two or more conductors,” and its use hereby acknowledged with thanks.
- 0.4 This standard is subject to periodical review in order to keep pace with the development in industry. Any suggestions for improvement shall be recorded and placed before the revising committee in due course.
- 0.5 This standard is intended chiefly to cover the technical provisions relating to this standard and it does not include all the necessary provisions of a Contract.

CONTENTS

FOREWORD	5
1 General	7
1.1 Scope	7
1.2 Normative references	7
2 Oil resistant, polyvinyl chloride sheathed, screened and unscreened flexible cable	9
2.1 Code designation	9
2.2 Rated voltage	9
2.3 Construction	9
2.4 Tests	13
2.5 Guide to use	15
Annex A (normative) Code designation	23
Table 1 – General data for type 60227 IEC 74	17
Table 2 – General data for type 60227 IEC 75	19
Table 3 – Tests for type 60227 IEC 74 and 60227 IEC 75	21

POLYVINYL CHLORIDE INSULATED CABLES OF RATED VOLTAGES UP TO AND INCLUDING 450/750 V –

Part 7: Flexible cables screened and unscreened with two or more conductors

1 General

1.1 Scope

This part of IEC 60227 details the particular specifications for polyvinyl chloride insulated, screened and unscreened control cables of rated voltages up to and including 300/500 V.

All cables comply with the appropriate requirements given in IEC 60227-1 and each individual type of cable complies with the particular requirements of this part.

1.2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60096-1:1986, *Radio-frequency cables – Part 1: General requirements and measuring methods*

IEC 60227-1:1993, *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 1: General requirements*

IEC 60227-2:1979, *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 2: Test methods*

IEC 60228:1978, *Conductors of insulated cables*

IEC 60332-1:1993, *Tests on electric cables under fire conditions – Part 1: Test on a single vertical insulated wire or cable*

IEC 60502-1:1997, *Power cables with extruded insulation and their accessories for rated voltages from 1 kV ($U_m = 1,2$ kV) up to 30 kV ($U_m = 36$ kV) – Part 1: Cables for rated voltages of 1 kV ($U_m = 1,2$ kV) and 3 kV ($U_m = 3,6$ kV)*

IEC 60719:1992, *Calculation of the upper and lower limits for the average outer dimensions of cables with circular copper conductors and of rated voltages up to and including 450/750 V*

IEC 60811-1-1:1993, *Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general applications – Section 1: Measurement of thickness and overall dimensions – Tests for determining the mechanical properties*

IEC 60811-1-2:1985, *Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general applications – Section 2: Thermal ageing methods*

IEC 60811-1-4:1985, *Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general applications – Section 4: Tests at low temperature*

IEC 60811-2-1:1986, *Common test methods for insulating and sheathing materials of electric cables – Part 2: Methods specific to elastomeric compounds – Section 1: Ozone resistance test – Hot set test – Mineral oil immersion test*

IEC 60811-3-1:1985, *Common test methods for insulating and sheathing materials of electric cables – Part 3: Methods specific to PVC compounds – Section 1: Pressure test at high temperature – Tests for resistance to cracking*

IEC 60811-3-2:1985, *Common test methods for insulating and sheathing materials of electric cables – Part 3: Methods specific to PVC compounds – Section 2: Loss of mass test – Thermal stability test*

2 Oil resistant, polyvinyl chloride sheathed, screened and unscreened flexible cable

2.1 Code designation

60227 IEC 74 for screened cable

60227 IEC 75 for unscreened cable

2.2 Rated voltage

300/500 V

2.3 Construction

2.3.1 Conductor

Number conductors: 2 to 60.

Preferred number of conductors: 2, 3, 4, 5, 6, 7, 12, 18, 27, 36, 48 and 60.

The conductors shall comply with the requirements given in IEC 60228 for class 5 conductors

2.3.2 Insulation

The insulation shall be polyvinyl chloride compound of type PVC/D (see IEC 60227-1) applied around each conductor.

The insulation thickness shall comply with the specified value given in column 2 of table 1 or 2. The insulation resistance shall be not less than the value given in table 1, column 8 or table 2, column 6.

2.3.3 Assembly of cores and fillers, if any

The cores shall be twisted together, where appropriate in several concentric layers.

A centre core is not permitted but a centre filler of suitable material shall be applied for cables with five or more cores in the first layer. Assemblies with three or more cores shall have one core which is coloured green and yellow.

Around each layer a tape may be applied which may cover the cores fully or partially. The tape shall not adhere to the cores.

For two-core cables, the space between the cores shall be filled either by separate fillers or by the sheath filling the interstices.

2.3.4 Inner sheath for screened cables

The inner sheath shall be a polyvinyl chloride compound of type PVC/ST5 (see IEC 60227-1) applied around the core assembly. For all cables, the thickness of the inner sheath shall be determined by the formula:

$$t_{is} = 0,02 D_f + 0,6 \text{ mm},$$

where D_f is the fictitious diameter over the laid-up core, calculated in accordance with A.2.1, A.2.2 and A.2.3 of IEC 60502, annex A, and where the fictitious diameter (d_f) of 0,5 mm², 0,75 mm² and 1,0 mm² conductors (not given in A.2.1) shall be taken to be 0,8 mm, 1,0 mm and 1,1 mm, respectively.

For cables with the preferred number of cores, the calculated values of the inner sheath thickness are given in column 3 of table 1.

NOTE In the case of cables comprising 10 or more cores, the values specified apply to a core assembly in two or more layers.

The mean value of the thickness of the sheath shall be not less than the calculated value. However, the thickness at any place may be less than the calculated value provided that the difference does not exceed 0,1 mm + 15 % of the calculated value.

The inner sheath may fill the interstices of the laid-up core assembly, but it shall not adhere to the cores.

2.3.5 Screen

For screened cables, the screen shall be applied over the inner sheath, in the form of a braid of plain or tinned copper wires.

For cables with the preferred number of cores, the diameter of the copper wires shall comply with the values given in column 4 of table 1.

For the other cables, the following maximum values apply:

- 0,16 mm for $d \leq 10,0$ mm
- 0,21 mm for $10,0 \text{ mm} < d \leq 20,0$ mm
- 0,26 mm for $20,0 \text{ mm} < d \leq 30,0$ mm
- 0,31 mm for $d > 30,0$ mm

where d is the fictitious diameter under the braid which is calculated by adding to the fictitious diameter over laid-up cores, twice the specified thickness of inner sheath.

The screening efficiency shall be determined by measuring the transfer impedance. The value obtained shall not exceed 250 Ω /km at 30 MHz.

2.3.6 Sheath or oversheath

The sheath or oversheath shall be polyvinyl chloride compound of type PVC/ST9 (see IEC 60227-1) applied either:

- as an oversheath around the screen of screened cables, or
- as an sheath around the laid-up cores of unscreened cables.

An optional tape may be applied between screen and oversheath.

For all cables the thickness of the sheath or oversheath shall be determined by the formula:

$$t_s = 0,08 d_L + 0,4 \text{ mm}$$

with a maximum value of 2,4 mm, where d_L is the fictitious diameter over the screen of the screened cables or over the laid-up core assembly of unscreened cables.

The fictitious diameter shall be calculated in accordance with IEC 60502-1, annex A and 2.3.4 of this standard. The increase in diameter due to the braided screen is four times the diameter of the braiding wire specified in column 4 of table 1.

For cables with the preferred numbers of cores, the calculated values of the sheath and oversheath thickness are given in column 5 of table 1 and in column 3 of table 2 (see note in 2.3.4). Both for sheath and oversheath, the thickness requirements apply as specified in 5.5.3 of IEC 60227-1.

In unscreened cables, the sheath may fill the interstices of the laid-up core assembly, but it shall not adhere to the cores. In screened cables, the oversheath shall fit closely but not adhere to the screen.

All cables shall have practically a circular cross-section.

2.3.7 Core identification

Except the green and yellow core, if any, all cores shall be identified by numbers in accordance with 4.2 of IEC 60227-1.

2.3.8 Overall diameter

The mean overall diameter of the cables shall be within the limits to be determined in accordance with IEC 60719. For cables with the preferred number of cores, the limits, according to IEC 60719 are given in columns 6 and 7 of table 1 or in columns 4 and 5 of table 2, (see note in 2.3.4).

2.4 Tests

Compliance with the requirements of 2.3 shall be checked by inspection and by the tests given in table 3.

2.5 Guide to use

The main purpose of these cables is for the interconnection of parts of machines used for manufacturing purposes, including machine tools and mechanical handling equipment. The cables are permitted for the direct connection to the mains. Continual flexing is not recommended for the screened cables. If any of these cables is not required to move during use, installation in conduits, trunking etc. is advised.

Screened cables are recommended in environments where a moderate level of electro-magnetic interference is encountered.

These cables are designed for use only inside buildings and where the ambient temperatures remain within the range of +5 °C to +40 °C.

Maximum rated conductor temperature in normal use: 70 °C.

Maximum sheath temperature: 60 °C.

Table 1 – General data for type 60227 IEC 74

1	2	3	4	5	6		8
					Mean overall diameter		
					Lower limit	Upper limit	
Number and nominal cross-sectional area of conductors mm ²	Insulation thickness specified value mm	Inner sheath thickness specified value mm	Maximum diameter of the wires of the screen mm	Over-sheath thickness specified value mm	mm	mm	Minimum insulation resistance at 70 °C MΩ·km
2 × 0,5	0,6	0,7	0,16	0,9	7,7	9,6	0,013
2 × 0,75	0,6	0,7	0,16	0,9	8,0	10,0	0,011
2 × 1	0,6	0,7	0,16	0,9	8,2	10,3	0,010
2 × 1,5	0,7	0,7	0,16	1,0	9,3	11,6	0,010
2 × 2,5	0,8	0,7	0,16	1,1	10,7	13,3	0,009
3 × 0,5	0,6	0,7	0,16	0,9	8,0	10,0	0,013
3 × 0,75	0,6	0,7	0,16	0,9	8,3	10,4	0,011
3 × 1	0,6	0,7	0,16	1,0	8,8	11,0	0,010
3 × 1,5	0,7	0,7	0,16	1,0	9,7	12,1	0,010
3 × 2,5	0,8	0,7	0,16	1,1	11,3	14,0	0,009
4 × 0,5	0,6	0,7	0,16	0,9	8,5	10,7	0,013
4 × 0,75	0,6	0,7	0,16	1,0	9,1	11,3	0,011
4 × 1	0,6	0,7	0,16	1,0	9,4	11,7	0,010
4 × 1,5	0,7	0,7	0,16	1,1	10,7	13,2	0,010
4 × 2,5	0,8	0,8	0,16	1,2	12,6	15,5	0,009
5 × 0,5	0,6	0,7	0,16	1,0	9,3	11,6	0,013
5 × 0,75	0,6	0,7	0,16	1,0	9,7	12,1	0,011
5 × 1	0,6	0,7	0,16	1,1	10,3	12,8	0,010
5 × 1,5	0,7	0,8	0,16	1,2	11,8	14,7	0,010
5 × 2,5	0,8	0,8	0,21	1,3	13,9	17,2	0,009
6 × 0,5	0,6	0,7	0,16	1,0	9,9	12,4	0,013
6 × 0,75	0,6	0,7	0,16	1,1	10,5	13,1	0,011
6 × 1	0,6	0,7	0,16	1,1	11,0	13,6	0,010
6 × 1,5	0,7	0,8	0,16	1,2	12,7	15,7	0,010
6 × 2,5	0,8	0,8	0,21	1,4	15,2	18,7	0,009
7 × 0,5	0,6	0,7	0,16	1,1	10,8	13,5	0,013
7 × 0,75	0,6	0,7	0,16	1,2	11,5	14,3	0,011
7 × 1	0,6	0,8	0,16	1,2	12,2	15,1	0,010
7 × 1,5	0,7	0,8	0,21	1,3	14,1	17,4	0,010
7 × 2,5	0,8	0,8	0,21	1,5	16,5	20,3	0,009
12 × 0,5	0,6	0,8	0,21	1,3	13,3	16,5	0,013
12 × 0,75	0,6	0,8	0,21	1,3	13,9	17,2	0,011
12 × 1	0,6	0,8	0,21	1,4	14,7	18,1	0,010
12 × 1,5	0,7	0,8	0,21	1,5	16,7	20,5	0,010
12 × 2,5	0,8	0,9	0,21	1,7	19,9	24,4	0,009
18 × 0,5	0,6	0,8	0,21	1,3	15,1	18,6	0,013
18 × 0,75	0,6	0,8	0,21	1,5	16,2	19,9	0,011
18 × 1	0,6	0,8	0,21	1,5	16,9	20,8	0,010
18 × 1,5	0,7	0,9	0,21	1,7	19,6	24,1	0,010
18 × 2,5	0,8	0,9	0,21	2,0	23,3	28,5	0,009
27 × 0,5	0,6	0,8	0,21	1,6	18,0	22,1	0,013
27 × 0,75	0,6	0,9	0,21	1,7	19,3	23,7	0,011
27 × 1	0,6	0,9	0,21	1,7	20,2	24,7	0,010
27 × 1,5	0,7	0,9	0,21	2,0	23,4	28,6	0,010
27 × 2,5	0,8	1,0	0,26	2,3	28,2	34,5	0,009
36 × 0,5	0,6	0,9	0,21	1,7	20,1	24,7	0,013
36 × 0,75	0,6	0,9	0,21	1,8	21,3	26,2	0,011
36 × 1	0,6	0,9	0,21	1,9	22,5	27,6	0,010
36 × 1,5	0,7	1,0	0,26	2,2	26,6	32,5	0,010
36 × 2,5	0,8	1,1	0,26	2,4	31,5	38,5	0,009
48 × 0,5	0,6	0,9	0,26	1,9	23,1	28,3	0,013
48 × 0,75	0,6	1,0	0,26	2,1	24,9	30,4	0,011
48 × 1	0,6	1,0	0,26	2,1	26,1	31,9	0,010
48 × 1,5	0,7	1,1	0,26	2,4	30,4	37,0	0,010
48 × 2,5	0,8	1,2	0,31	2,4	35,9	43,7	0,009
60 × 0,5	0,6	1,0	0,26	2,1	25,5	31,1	0,013
60 × 0,75	0,6	1,0	0,26	2,2	27,0	32,9	0,011
60 × 1	0,6	1,0	0,26	2,3	28,5	34,7	0,010
60 × 1,5	0,7	1,1	0,26	2,4	32,7	39,9	0,010
60 × 2,5	0,8	1,2	0,31	2,4	38,8	47,2	0,009

Table 2 – General data for type 60227 IEC 75

1	2	3	4		6
			5		
			Lower limit	Upper limit	
Number and nominal cross-sectional area of conductors mm ²	Insulation thickness specified value mm	Sheath thickness specified value mm	Mean overall diameter		Minimum insulation resistance at 70 °C MΩ·km
			mm	mm	
2 × 0,5	0,6	0,7	5,2	6,6	0,013
2 × 0,75	0,6	0,8	5,7	7,2	0,011
2 × 1	0,6	0,8	5,9	7,5	0,010
2 × 1,5	0,7	0,8	6,8	8,6	0,010
2 × 2,5	0,8	0,9	8,2	10,3	0,009
3 × 0,5	0,6	0,7	5,5	7,0	0,013
3 × 0,75	0,6	0,8	6,0	7,6	0,011
3 × 1	0,6	0,8	6,3	8,0	0,010
3 × 1,5	0,7	0,9	7,4	9,4	0,010
3 × 2,5	0,8	1,0	9,0	11,2	0,009
4 × 0,5	0,6	0,8	6,2	7,9	0,013
4 × 0,75	0,6	0,8	6,6	8,3	0,011
4 × 1	0,6	0,8	6,9	8,7	0,010
4 × 1,5	0,7	0,9	8,2	10,2	0,010
4 × 2,5	0,8	1,1	10,1	12,5	0,009
5 × 0,5	0,6	0,8	6,8	8,6	0,013
5 × 0,75	0,6	0,9	7,4	9,3	0,011
5 × 1	0,6	0,9	7,8	9,8	0,010
5 × 1,5	0,7	1,0	9,1	11,4	0,010
5 × 2,5	0,8	1,1	11,0	13,7	0,009
6 × 0,5	0,6	0,9	7,6	9,6	0,013
6 × 0,75	0,6	0,9	8,1	10,1	0,011
6 × 1	0,6	1,0	8,7	10,8	0,010
6 × 1,5	0,7	1,1	10,2	12,6	0,010
6 × 2,5	0,8	1,2	12,2	15,1	0,009
7 × 0,5	0,6	0,9	8,3	10,4	0,013
7 × 0,75	0,6	1,0	9,0	11,3	0,011
7 × 1	0,6	1,0	9,5	11,8	0,010
7 × 1,5	0,7	1,2	11,3	14,1	0,010
7 × 2,5	0,8	1,3	13,6	16,8	0,009
12 × 0,5	0,6	1,1	10,4	12,9	0,013
12 × 0,75	0,6	1,1	11,0	13,7	0,011
12 × 1	0,6	1,2	11,8	14,6	0,010
12 × 1,5	0,7	1,3	13,8	17,0	0,010
12 × 2,5	0,8	1,5	16,8	20,6	0,009
18 × 0,5	0,6	1,2	12,3	15,3	0,013
18 × 0,75	0,6	1,3	13,2	16,4	0,011
18 × 1	0,6	1,3	14,0	17,2	0,010
18 × 1,5	0,7	1,5	16,5	20,3	0,010
18 × 2,5	0,8	1,8	20,2	24,8	0,009
27 × 0,5	0,6	1,4	15,1	18,6	0,013
27 × 0,75	0,6	1,5	16,2	19,9	0,011
27 × 1	0,6	1,5	17,0	21,0	0,010
27 × 1,5	0,7	1,8	20,3	24,9	0,010
27 × 2,5	0,8	2,1	24,7	30,2	0,009
36 × 0,5	0,6	1,5	17,0	20,9	0,013
36 × 0,75	0,6	1,6	18,2	22,4	0,011
36 × 1	0,6	1,7	19,4	23,8	0,010
36 × 1,5	0,7	2,0	23,0	28,2	0,010
36 × 2,5	0,8	2,3	28,0	34,2	0,009
48 × 0,5	0,6	1,7	19,8	24,3	0,013
48 × 0,75	0,6	1,8	21,2	25,9	0,011
48 × 1	0,6	1,9	22,5	27,6	0,010
48 × 1,5	0,7	2,2	26,2	32,5	0,010
48 × 2,5	0,8	2,4	32,1	39,1	0,009
60 × 0,5	0,6	1,8	21,7	26,6	0,013
60 × 0,75	0,6	2,0	23,4	28,7	0,011
60 × 1	0,6	2,1	24,9	30,5	0,010
60 × 1,5	0,7	2,4	29,5	35,8	0,010
60 × 2,5	0,8	2,4	35,0	42,6	0,009

Table 3 – Tests for type 60227 IEC 74 and 60227 IEC 75

1	2	3	4	5
Ref. no.	Tests	Category of test	Test method described in: IEC Standard	Subclause
1	<i>Electrical test</i>			
1.1	Resistance of conductors	T, S	60227-2	2.1
1.2	Voltage test on cores according to specified insulation thickness			
1.2.1	At 1 500 V $\leq 0,6$ mm	T	60227-2	2.3
1.2.2	At 2 000 V $> 0,6$ mm	T	60227-2	2.3
1.3	Voltage test on completed cable at 2 000 V	T, S	60227-2	2.2
1.4	Insulation resistance at 70 °C	T	60227-2	2.4
1.5	Transfer impedance for screened cables	T	60096-1	A.5.1 and A.5.2
2	<i>Provisions covering constructional and dimensional characteristics</i>		60227-1 and 60227-2	
2.1	Checking of compliance with constructional provisions	T, S	60227-1	Inspection and manual test
2.2	Measurements of insulation thickness	T, S	60227-2	1.9
2.3	Measurements of thickness of sheath or inner sheath or oversheath	T, S	60227-2	1.10
2.4	Measurement of overall diameter			
2.4.1	Mean value	T, S	60227-2	1.11
2.4.2	Ovality	T, S	60227-2	1.11
3	<i>Mechanical properties of insulation</i>			
3.1	Tensile test before ageing	T	60811-1-1	9.1
3.2	Tensile test after ageing	T	60811-1-2	8.1.3
3.3	Loss of mass test	T	60811-3-2	8.1
4	<i>Mechanical properties of inner sheath</i>			
4.1	Tensile test before ageing	T	60811-1-1	9.2
4.2	Tensile test after ageing	T	60811-1-2	8.1.3.1
5	<i>Mechanical properties of sheath or oversheath</i>			
5.1	Tensile test before ageing	T	60811-1-1	9.2
5.2	Tensile test after ageing	T	60811-1-2	8.1
5.3	Loss of mass test	T	60811-3-2	8.2
6	<i>Compatibility test</i> ¹⁾	T	60811-1-2	8.1.4
7	<i>Pressure test at high temperature</i>			
7.1	Insulation	T	60811-3-1	8.1
7.2	Sheath or oversheath	T	60811-3-1	8.2
8	<i>Test at low temperature</i>			
8.1	Bending test for insulation	T	60811-1-4	8.1
8.2	Bending test for sheath or oversheath ²⁾	T	60811-1-4	8.2
8.3	Elongation test for sheath or oversheath ³⁾	T	60811-1-4	8.4
8.4	Impact test ⁴⁾	T	60811-1-4	8.5
9	<i>Heat shock test</i>			
9.1	Insulation	T	60811-3-1	9.1
9.2	Sheath or oversheath	T	60811-3-1	9.2
10	<i>Mechanical strength of completed cable</i>			
10.1	Flexing test for unscreened cable ⁵⁾	T	60227-2	3.1
11	<i>Test of flame retardance</i>	T	60332-1	
12	<i>Mineral oil resistance of sheath or oversheath</i>	T	60811-2-1	10
¹⁾ If applicable, see 5.3.1 of IEC 60227-1. ²⁾ Only applicable to cables having mean overall diameters up to and including 12,5 mm. ³⁾ Only applicable if the mean overall diameter of the cable exceeds 12,5 mm. ⁴⁾ The inner sheath of screened cables shall also be checked. ⁵⁾ Not applicable to cables with more than 18 cores.				

Annex A (normative)

Code designation

Cables of the types covered by this standard are designated by two numerals, preceded by the reference number of this standard.

The first numeral indicates the basic class of cable; the second numeral indicates the particular type within the basic class.

The classes and types are as follows:

0. Non-sheathed cables for fixed wiring.
 01. Single-core non-sheathed cable with rigid conductor for general purposes (60227 IEC 01).
 02. Single-core non-sheathed cable with flexible conductor for general purposes (60227 IEC 02).
 05. Single-core non-sheathed cable with solid conductor for internal wiring for a conductor temperature of 70 °C (60227 IEC 05).
 06. Single-core non-sheathed cable with flexible conductor for internal wiring for a conductor temperature of 70 °C (60227 IEC 06).
 07. Single-core non-sheathed cable with solid conductor for internal wiring for a conductor temperature of 90 °C (60227 IEC 07).
 08. Single-core non-sheathed cable with flexible conductor for internal wiring for a conductor temperature of 90 °C (60227 IEC 08).
1. Sheathed cables for fixed wiring.
 10. Light polyvinyl chloride sheathed cable (60227 IEC 10).
4. Non-sheathed flexible cables for light duty.
 41. Flat tinsel cord (60227 IEC 41).
 42. Flat non-sheathed cord (60227 IEC 42).
 43. Cord for decorative chains (60227 IEC 43).
5. Sheathed flexible cables for normal duty.
 52. Light polyvinyl chloride sheathed cord (60227 IEC 52).
 53. Ordinary polyvinyl chloride sheathed cord (60227 IEC 53).
 56. Heat-resistant light PVC-sheathed cord for a maximum conductor temperature of 90 °C (60227 IEC 56).
 57. Heat-resistant ordinary PVC-sheathed cord for a maximum conductor temperature of 90 °C (60227 IEC 57).
7. Sheathed flexible cables for special duty.
 - 71f. Flat polyvinyl chloride sheathed lift cables and cables for flexible connections (60227 IEC 71f).
 74. Oil resistant polyvinyl chloride sheathed, screened flexible cable (60227 IEC 74).
 75. Oil resistant, polyvinyl chloride sheathed unscreened flexible cable (60227 IEC 75).